

Docket No. 1948-4293US1**IN THE CLAIMS**

1. (Currently Amended) A friction material designed for fitting to a device employing friction in a liquid medium, the friction material comprising
approximately 20% to 40% by weight a mat of non-woven fibres,
approximately 40% to 60% by weight a thermosetting resin which impregnates said fibres, wherein the fibres have a length of at least 12 mm, and
filler ranging by weight between ~~a nonzero percentage proximate 0%~~
approximately 1% and approximately 40%, wherein the non-woven fibres and the resin are found in specific proportions with the filler.
2. (Previously Amended) A friction material according to Claim 1, wherein the average length of the fibres is at most 120 mm.
3. (Previously Amended) A friction material according to Claim 2, wherein the fibres are chosen from the group consisting of glass, wool, cotton, ceramic, polyacrylonitrile, preoxidized polyacrylonitrile and aramid.
4. (Previously Amended) A friction material according to Claim 3, wherein the filler is in powder form and incorporated into the mat.
5. (Previously Amended) A friction material according to Claim 4, wherein the filler is selected from the group consisting of copper, rockwool, carbon, zirconium silicate, iron sulphide, alumina, rubber and diatoms.
6. (Previously Amended) A friction material according to Claim 4, wherein the filler is in the form of pulps and incorporated into the mat.
7. (Previously Amended) A friction material according to Claim 6, wherein the filler is selected from the group consisting of the pulps of glass, aramid, acrylic and phenolic fibres.

Docket No. 1948-4293US1

8. (Previously Canceled)

9. (Previously Amended) A friction material according to Claim 1, wherein the thermosetting resin is resol-based.

10. (Previously Amended) A friction material according to Claim 1, wherein latex is added to the thermosetting resin.

11. (Previously Amended) A friction material according to Claim 1, wherein the filler is in powder form and incorporated into the thermosetting resin, and wherein the filler is selected from the group consisting of copper, rockwool, carbon, zirconium silicate, iron sulphide, alumina, rubber and diatoms.

25. (Previously Amended) A friction material according to Claim 5, wherein the filler is in form of pulps and incorporated into the mat.

26 (Previously Canceled)

28. (Previously Amended) A friction material according to Claim 1, wherein the thermosetting resin includes a polar solvent, the polar solvent being an aqueous polar solvent.

33. (Currently Amended) A friction material for a device employing friction in a liquid medium, the friction material comprising a mat of non-woven fibres impregnated with a thermosetting resin, wherein the friction material comprises by weight

approximately 20% to 40% fibres selected from the group consisting of glass, wool, cotton, ceramic, polyacrylonitrile, preoxidized polyacrylonitrile and aramid;

approximately 40% to 60% thermosetting resin selected from the group consisting of water-based resins, resol-based resins, phenolic plastic resins, aminoaldehyde resins, epoxy resins and polyimide resins; and

~~a non-zero percentage proximate 0%~~ to approximately 1% to 40% filler, wherein

Docket No. 1948-4293US1

the fibres and the thermosetting resin are found in specific proportions with the filler.

34. (Previously Added) The friction material according to Claim 33 wherein the fibres have an average length of between approximately 12 mm and 120 mm.

35. (Previously Added) The friction material according to Claim 33 that is by weight approximately 20% glass fibres, 10% ceramic fibres, 10% polyacrylonitrile fibres, and 60% water-based resin.

36. (Previously Added) The friction material according to Claim 33 that is by weight approximately 30% cotton fibres, 10% ceramic fibres, and 60% water-based resin

37 (Previously Amended) The friction material according to Claim 33, wherein the filler is selected from the group consisting of copper, rockwool, carbon, zirconium silicate, iron sulphide, alumina, rubber, diatoms, glass, aramid, acrylic and phenolic fibres.

38. (Previously Added) The friction material according to Claim 37 that is by weight approximately 20% glass fibres, 10% ceramic fibres, 10% polyacrylonitrile fibres, 10% carbon, 10% coke, and 40% resol-based resin.

39. (Previously Amended) The friction material according to Claim 37 that is by weight approximately 20% glass fibres, 10% ceramic fibres, 10% polyacrylonitrile fibres, 10% copper, 10% rockwool, and 40% resol-based resin.

Docket No. 1948-4293US1

Reduced Fees Under 37 C.F.R. §1.9(f) paid herewith \$

- ☐ _____ Pages Sequence Listing
- ☐ _____ Computer disk(s) containing substitute Sequence Listing
- ☐ Statement under 37 C.F.R. §1.825(b) that the computer and paper copies of the substitute Sequence Listing are the same.
- ☐ A check in the amount of \$_____ to cover the filing fee is attached.
- ☐ Charge fee to Deposit Account No. 13-4500, Order No. _____. A DUPLICATE COPY OF THIS SHEET IS ATTACHED.
- ☒ The Commissioner is hereby authorized to charge any additional fees which may be required for filing this amendment, including all fees pursuant to 37 CFR §1.17 for its timely consideration, or credit any overpayment to Deposit Account No. 13-4500, Order No. 1948-4293US1. A DUPLICATE COPY OF THIS SHEET IS ATTACHED.

Respectfully submitted
MORGAN & FINNEGAN, L.L.P.

Dated: August 14, 2003By: 

David M La Bruno
Registration No. 46,266

Correspondence Address:

MORGAN & FINNEGAN, L.L.P.
345 Park Avenue
New York, NY 10154-0053
(212) 758-4800 Telephone
(212) 751-6849 Facsimile